

PRODUCT LIST Technical Data Sheet updated 05/2016

	adicional Code	finish	thickness	reference number	light transmission	total solar transmission	total solar reflection	total solar energy absorbed	solar energy rejected	visible light reflection	UV rejection	ABG-Nr.
		hardcoat	[μ] approx.		%	%	%	%	%	%	%	
Automotive Films												
Best Bond												
SL® Automotive film	Best Bond 05	sr	50	38310	5	14	9	77	62	6	99	D5608
SL® Automotive film	Best Bond 12	sr	50	38320	12	24	8	68	55	6	99	D5608
SL® Automotive film	Best Bond 28	sr	50	38330	35	35	8	57	48	8	99	D5608
Royal Bond												
SL® Automotive film	Royal Bond 05	sr	50	38830	5	24	12	64	60	10	99	D5579
SL® Automotive film	Royal Bond 19	sr	50	38840	19	33	13	54	53	10	99	D5578
SL® Automotive film	Royal Bond 34	sr	50	38850	36	42	11	47	46	11	99	D5578
SL® Automotive film	Royal Bond 49	sr	50	38860	49	46	12	42	43	11	99	D5578
Pure Bond												
SL® Automotive film	Pure Bond 05	sr	50	38870	4	42	8	50	45	8	99	D5580
SL® Automotive film	Pure Bond 19	sr	50	38880	19	47	8	45	41	8	99	D5580
SL® Automotive film	Pure Bond 34	sr	50	38890	34	50	8	42	39	8	99	D5580
SL® Automotive film	Pure Bond Black 05	sr	50	38865	6	39	7	54	44	8	99	D5589
SL® Automotive film	Pure Bond Grey 15	sr	34	38835	15	54	7	39	40	8	99	D5581
Ceramic Bond												
SL® Automotive film *	Ceramic Bond 05	sr	50	38220	5	5	8	87	70	8	99	*
SL® Automotive film *	Ceramic Bond 20	sr	50	38230	19	11	6	83	65	7	99	*
SL® Automotive film *	Ceramic Bond 40	sr	40	38240	43	24	7	69	60	10	99	*
SL® Automotive film *	Ceramic Bond 50	sr	40	38560	52	27	5	68	57	5	99	*
SL® Automotive film *	Ceramic Bond 70	sr	40	38270	70	34	8	58	50	9	99	*
Specials												
SL® Automotive film	Alu Bond 05	sr	60	38400	5	13	31	56	71	13	99	D5317
SL® Automotive film	Alu Bond 20	sr	50	38160	20	27	20	53	47	9	99	D5146
SL® Automotive film	Chrome Bond 20	sr	50	38120	20	28	26	46	59	24	99	D5146
OPALFILM®	Saphire dark 3AF	sr	50	38110	3	7	33	60	73	18	99	D5146
SL® Automotive film	Spectra Bond	sr	50	38030	70	49	27	24	45	15	99	D5531
SL® Auto- shatter film	Secure Bond 100	sr	115	38900	89	81	9	10	16	8	99	D5532
SL® Auto- shatter film	Secure Bond 175	sr	190	38910	88	81	9	10	18	8	99	D5533
SL® Auto- shatter film	Secure Bond 360	sr	360	38920	84	81	9	10	19	8	99	D5582
SL® paint protection film	Protect Bond 180 PVC Basic	sr	180	39965								
SL® paint protection film	Protect Bond 200 TPU Premium	sr	200	39960								